


# DEKTITE<sup>®</sup> AND RETROFIT DEKTITE<sup>®</sup> Pipe Flashings

## Product Specifications

**Pipe Diameter Ranges**..... 1/4" to 18" - Dektite  
                                               3/4" to 10" - Retrofit Dektite  
                                               1/4" to 18" - Silicone

**Materials**.....EPDM - Standard and Retrofit  
                                               Silicone - High Temperature



Standard Dektite



Retrofit Dektite

## Performance Data

| ASTM Method | Test Description                   | Specification   | Test Results |
|-------------|------------------------------------|-----------------|--------------|
| D412        | Tensile Strength (min. psi rating) | 1450 psi min.   | 1537 psi     |
| D412        | Ultimate Elongation (%)            | 350 min.        | 535          |
| D1171       | Resistance to Ozone-min. rating    | 100 (no cracks) | Passed       |
| D673        | Heat Aging - 70 hrs. at 212°F      |                 |              |
|             | • Change in Hardness (points)      | ± 15 max.       | +8           |
|             | • Change in Tensile Strength (%)   | ± 30 max.       | -4.7         |
|             | • Change in Elongation (%)         | ± 50 max.       | -26          |

| ASTM Method | Test Description                                    | Specification                | Test Results |
|-------------|-----------------------------------------------------|------------------------------|--------------|
| D2137       | Low Temperature Brittleness - 3 mins. at -40°F      | Non-brittle                  | Passed       |
| D624        | Tear Resistance Die C (min.) per inch of width min. | 125 pounds per inch of width | 130 pounds   |
| U.L. 94     | Flame Resistance                                    | U.L. 94 H.B.                 | Passed       |